

FACETED EPOXY COLOR

1	2	3	4	5	6	7	8	9	10	11	12
13	14	15	16	17	18	19	20	21	22	23	24
37	38	39	40	41	42	43	44	45	46	47	48
61	62	63	64	65	66	67	68	69	70	71	72
73		75	76		78	79	80	81	82	83	84
85	86	87	88	89	90	91	92	93	94	95	96
97	98	99	100	101	102	103	104	105	106		
	110	111	112	113	114	115					

** color tone can be changeable depending on production time

** conditions for pressing Faceted Epoxyn(Back side)

** pressure :2.8~3.0kg

** Temperature :160~170

** Time :8~10 seconds (small size) more than 15seconds (big size)